
Polycure Tips & Insights: Recoating Timber, Parquetry or Cork

1. Clean floor with AQUACARE 8440 Floor Clean Concentrate or AQUACARE 8430 Floor Clean & Degreaser.
2. Sand floor with 120-150 grade sandpaper or screen back on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly. Take care to avoid scratching the surface.
3. Apply the chosen coating per the directions on the product datasheet.
4. Optional: Apply a second coat of the chosen coating.

Warning: All coatings provide protection for the substrate; however, no coating is indestructible, and all coatings will mark or scratch. Sharp objects including sand and grit will scratch the surface of any coated floor. In high traffic commercial environments such as hairdressing salons, night clubs or taverns several factors need to be considered when choosing a coating system such as the amount of traffic, moisture, alcohol and chemicals likely to come into contact with the floor. A thorough cleaning and maintenance program must be implemented after the coating system has thoroughly dried to help to maintain the coating.

PLEASE CONTACT POLYURE'S TECHNICAL SERVICE DEPARTMENT OR YOUR LOCAL POLYURE ACCOUNT EXECUTIVE FOR FURTHER FREE ADVICE.

www.polycure.com.au